

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 812 863 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
15.09.1999 Bulletin 1999/37

(51) Int Cl.⁶: **C08F 20/12, C08F 2/30**

(21) Application number: **97109582.3**

(22) Date of filing: **12.06.1997**

(54) **Acrylic emulsions prepared in the presence of fully hydrolyzed poly(vinyl alcohol)**

Acrylemulsionen hergestellt in gegenwart von vollständig hydrolysiertem Poly(vinylalcohol)

Emulsions acryliques préparés en présence de poly(vinylalcohol) entièrement hydrolysé

(84) Designated Contracting States:
DE GB IT NL

(30) Priority: **14.06.1996 US 663496**

(43) Date of publication of application:
17.12.1997 Bulletin 1997/51

(73) Proprietor: **AIR PRODUCTS AND CHEMICALS,
INC.**
Allentown, PA 18195-1501 (US)

(72) Inventors:
• **Bott, Richard Henry**
Macungie, PA 18062 (US)
• **Distefano, Frank Vito**
Macungie, PA 18062 (US)

(74) Representative: **Kador & Partner**
Corneliusstrasse 15
80469 München (DE)

(56) References cited:
EP-A- 0 450 437 **US-A- 5 364 904**

- **DATABASE WPI Week 9531 Derwent**
Publications Ltd., London, GB; AN 88-238770
XP002041366 "DISPERSION STABILISER FOR
VINYL CPD. EMULSION POLYMERISATION
COMPRISES MIXT. OF POLYVINYL ALCOHOL
OF LOW POLYMERISATION DEGREE " & JP 63
171 628 A (KURARAY CO LTD) , 15 July 1988

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 812 863 B1

Description

TECHNICAL FIELD OF THE INVENTION

5 [0001] This invention relates to a process for preparing stable emulsions of polyacrylates in the presence of poly(vinyl alcohol) and to the resulting emulsion.

BACKGROUND OF THE INVENTION

10 [0002] Poly(vinyl alcohol) is a widely used stabilizer for the emulsion polymerization of many vinyl ester monomers. The use of poly(vinyl alcohol) as a stabilizer allows for particle size control, rheology and crosslinking characteristics which are valuable for applications such as adhesives, sealants, coatings and binders. One limitation has been the inability to prepare stable acrylic emulsions at relatively low stabilizer levels of poly(vinyl alcohol), e.g., less than 12% by weight of the acrylic monomer to be polymerized. Another limitation of poly(vinyl alcohol) has been the inability of
15 the industry to expand the use of this as a stabilizer for acrylic emulsions having high solids, e.g., greater than 45% by weight. Many efforts have been made to overcome this limitation, and in doing so all have generally relied either on process or compositional changes.

[0003] The following patents and references comment on the use of poly(vinyl alcohol) as a stabilizer system for the emulsion polymerization of a monomer mixture consisting of monomers having acrylic unsaturation.

20 [0004] GB 1348449 and Farmer, D. B. in "Polyvinyl alcohol-Developments", C. A. Finch ed. John Wiley & Sons, New York, NY, (p. 459, 1992) disclose the preparation of acrylic emulsions using non ionic or anionic surface active agents. Poly(vinyl alcohol) by itself, is alleged as being unsuitable for producing a stable emulsion.

[0005] US 5,326,809 discloses the use of poly(vinyl alcohol-co-vinyl amine) as a stabilizer for the emulsion polymerization of a wide range of ethylenically unsaturated monomers. A representative poly(vinyl alcohol-co-vinyl amine) stabilizer contained from 50 to 99 mole % poly(vinyl alcohol) and from 0.1 to 50% poly(vinyl amine). All of the examples
25 where acrylic monomers were exclusively used showed the addition of surfactant to enhance emulsion stability. Some stability enhancement was achieved through the amine functionality. Also, the acrylic monomer was methyl acrylate which in itself is easier to stabilize with PVOH because of its greater water solubility.

[0006] US 5,354,803 discloses the preparation of a surfactantless formaldehyde-free poly(vinyl alcohol) graft copolymer comprising from 12 to 35% of a fully hydrolyzed low molecular weight poly(vinyl alcohol). In that work, a high concentration (12-35% by weight) of poly(vinyl alcohol) was used to promote chemical grafting of the acrylic monomer to the poly(vinyl alcohol). In addition, the solids contents of the emulsions prepared were consistently less than 40% by weight.

[0007] US 5,364,904 discloses the preparation of a copolymer emulsion for use as a sizing agent for glass fibers. The emulsion is formed by microfluidizing an emulsion containing an alkyl (-meth) acrylate monomer and stabilized with poly(vinyl alcohol). The poly(vinyl alcohol) preferably has a degree of hydrolysis of at least 70% although no criticality of the hydrolysis of the poly(vinyl alcohol) is stated. The examples show the addition of surfactant which undoubtedly promotes stability of the emulsion.

[0008] GB 1,438,449 disclose the use of poly(vinyl alcohol) containing acid or mercaptan groups as a means for stabilizing all acrylic emulsion compositions. In addition, this reference also point out the lack of utility in using conventional poly(vinyl alcohol) as the stabilizer for all acrylic emulsion compositions.

[0009] US 4,670,505 discloses the use of low molecular weight amino alcohols as part of a stabilization system for emulsion polymerization of (meth)acrylic monomers in the presence of protective colloids and surfactants. Preparing acrylic systems without vinyl acetate present in an amount of at least 50% resulted in unstable systems when prepared
45 in the presence of poly(vinyl alcohol).

[0010] US 2,318,429 discloses a process for producing an aqueous dispersion of polymerized alkyl methacrylates, i.e., methylmethacrylate, and isobutyl acrylate using a partially saponified polyvinyl acetate as a dispersing agent. The patentee noted that aqueous dispersions of polyacrylates had been obtained with anionic surface active agents but these emulsions had limited utility as textile finishes because they are readily coagulated by cationic surface active agents, by polyvalent metal ions and by positively charged emulsions and dispersions. The patentees reported that colloidal systems could be prepared by polymerizing alkyl acrylates in the presence of a partially saponified polyvinyl acetate having a saponification number of from 40-130 and a viscosity of approximately 20 centipoises (4% aqueous solution at 20°C). Table 1 discloses the preparation of polymethylmethacrylate and the presence of partially saponified and completely saponified polyvinyl acetate. The patentee noted that the emulsions prepared with completely saponified polyvinyl acetate were unstable.

55 [0011] US 2,407,107 discloses a process for producing stable dispersions of alkyl acrylate polymers by an emulsion polymerization process wherein the alkyl acrylate monomers are emulsified in an aqueous solution and polymerized. A water soluble, partially saponified polyvinyl acetate is used as the emulsifying agent and is accompanied with a small

amount of a petroleum hydrocarbon such as a mineral oil or wax. The hydrocarbon is employed in an amount from 0.5-5% based on the weight of alkyl acrylate monomer and is used for enhancing the stability of the emulsion which contains typically from 10-40% by weight of polymerized alkyl acrylate.

[0012] US 2,773,050 discloses a process for polymerizing an acrylic ester while in admixture with a polymer containing hydroxyl radicals, e.g., poly(vinyl alcohol) which then can be hardened by treatment with a crosslinking agent. The polymerization is advantageously carried out by preparing a dispersion of acrylic ester in an aqueous solution of a vinyl polymer having hydroxyl radicals, e.g., poly(vinyl alcohol) and, optionally, an emulsifying agent, e.g., alkali metal salts of sulfated fatty alcohol. The weight ratio of acrylic resin to the poly(vinyl alcohol) and the emulsion ranges from 80:20 to 50:50 although preferably from 80:20 to 65:35.

SUMMARY OF THE INVENTION

[0013] This invention pertains to improved acrylic emulsion compositions and to an improved process for preparing an acrylic emulsion. The improvement for polymerizing water insoluble acrylic monomer systems resides in effecting the polymerization of the acrylic monomers in the presence of a stabilizer system consisting essentially of poly(vinyl alcohol) having specified hydrolysis levels and in the presence of a chain transfer agent. This medium allows for the preparation of emulsions with useful properties and suited for use in applications such as adhesives, coatings, binders and cement additives. It has been found that it is possible to polymerize a substantially all acrylic, water insoluble monomer system wherein at least a majority of the acrylic monomer has a carbon content greater than methyl acrylate and stabilize that all acrylic emulsion system at high solids, greater than 45% by weight, at concentrations of less than 12% poly(vinyl alcohol) by weight of the emulsion using a stabilizer consisting essentially of poly(vinyl alcohol) selected from the group consisting of substantially fully hydrolyzed poly(vinyl alcohol) and a poly(vinyl alcohol) having a hydrolysis value of at least 86% and a molecular weight of from 5,000 to 13,000. Hydrolysis levels of less than 96.5% may be used in low molecular weight poly(vinyl alcohols) whereas higher molecular weight poly(vinyl alcohols) lead to instability.

[0014] There are several advantages associated with the invention and these include:

- an ability to produce high solids, essentially all acrylic emulsions using poly(vinyl alcohol) protective colloid as a stabilizer;
- an ability to produce acrylic emulsions having relatively low levels of poly(vinyl alcohol), e.g., from 2 to 12% and generally within a range of 3 to 5% by weight of the monomers;
- an ability to produce stable acrylic emulsions without the use of conventional surfactants or hydrocarbon solubilizers or microfluidization techniques;
- an ability to produce acrylic emulsions having excellent adhesion to a variety of substrates such as wood and having excellent wet strength and water resistance;
- an ability to form excellent films and coatings;
- an ability to produce redispersible acrylic polymers stabilized with poly(vinyl alcohol); and,
- an ability to produce acrylic emulsions having low viscosities.

DETAILED DESCRIPTION OF THE INVENTION

[0015] In the practice of this invention, substantially all acrylic emulsions can be produced by an emulsion polymerization process using a stabilizer system consisting of poly(vinyl alcohol) as the stabilizer. Acrylic monomers, particularly those acrylic monomers which have a water insolubility less than that of methyl acrylate, have been essentially impossible to polymerize in an emulsion system using poly(vinyl alcohol) as the stabilizer.

[0016] A wide range of acrylic monomers can be used in the polymerization process described herein and they may be used singly or in combination with other acrylic monomers. These ethylenically unsaturated polymerizable C₁-C₈ alkyl esters of acrylic and methacrylic acid include methylacrylate, ethylacrylate, butylacrylate, 2-ethyl-hexyl acrylate and the corresponding methacrylates. Of these methylmethacrylate and butylacrylate are the preferred lower alkyl acrylates used in the polymerization process for producing a variety of polymeric systems suited for adhesive, coating, binder and cementitious applications.

[0017] Other ethylenically unsaturated monomers may be copolymerized with the acrylic esters. The composition of the resultant copolymer is largely dependent upon the application. Typical monomers include vinyl acetate, acrylamide, methacrylamide, acrylic and methacrylic acid, maleic and fumaric anhydride, and so forth. The slightly more water soluble acrylates which include hydroxy acrylates, e.g., hydroxy ethyl acrylate and glycidyl acrylates may also be copolymerized with the acrylic esters. Monomers other than the acrylic esters should be kept to a minimum in order for the emulsion to be considered an acrylic emulsion, e.g., below 10% and preferably below 5% by weight of the monomers employed in producing the polymer. The more hydrophilic monomers, i.e., monomers which are more hydrophilic than

the acrylic monomers to be polymerized, should be avoided to maintain water resistant properties.

[0018] One of the keys to producing a high solids, e.g., greater than 45% by weight all acrylic emulsion without the use of surfactants, solubilizers, and microfluidization techniques resides in the use of a poly(vinyl alcohol) selected from the group consisting of substantially fully hydrolyzed poly(vinyl alcohol) and a partially hydrolyzed poly(vinyl alcohol), > 86%, as the stabilizing agent where the molecular weight ranges from 5,000 to 13,000. Low molecular weight poly(vinyl alcohols), i.e., below 13,000 may be used upwards from the 86% hydrolyzed to fully hydrolyzed. The level of poly(vinyl alcohol) utilized as a stabilizer is from 2 to 12%, preferably from 3 to 7% based on the weight of the total monomers polymerized. One type of poly(vinyl alcohol) has a hydrolysis value of at least 96.5%, i.e., 96.5% of the acetate groups in poly(vinyl acetate) are converted to hydroxyl groups. When less than 96.5% of the acetate groups are converted to hydroxyl groups, i.e., the polyvinyl acetate is less than fully hydrolyzed, and the molecular weight is above 13,000, there is a tendency for a high solids acrylic emulsion formulation to become gritty. As the degree of hydrolysis is reduced substantially below 96.5%, the latex may become unstable. A second type of poly(vinyl alcohol) is a poly(vinyl alcohol) having a hydrolysis value of at least 86% to fully hydrolyzed and a molecular weight within a range of from 5,000 to 13,000. Poly(vinyl alcohols) having lower hydrolysis values and high molecular weights may be acceptable for producing low solids acrylic emulsions as noted by the prior art but they are incapable of producing high solids emulsions at low poly(vinyl alcohol) stabilizer levels.

[0019] The molecular weight of the poly(vinyl alcohol) is an important factor in stabilizing the acrylic emulsion. A fully hydrolyzed poly(vinyl alcohol) having a number average molecular weight within a range of from 5,000 to 45,000 should be used with a preferred range of from 15,000 to 30,000. The lower hydrolysis value poly(vinyl alcohols) may be used provided the molecular weight does not exceed about 13,000.

[0020] Blends of fully hydrolyzed poly(vinyl alcohols) may be used with favorable results. One type of blend comprises from 20 to 80%, preferably 50 to 75%, of a low molecular weight (5,000 to 13,000) poly(vinyl alcohol), including 86 to 90% hydrolyzed, and 20 to 80%, preferably 50 to 25%, of a higher molecular weight, e.g., 25,000 to 45,000 molecular weight poly(vinyl alcohol). Another blend may comprise a fully hydrolyzed poly(vinyl alcohol) and a partially hydrolyzed poly(vinyl alcohol) which by itself would have been unacceptable for stabilizing the emulsion. In other words, not all of the stabilizing poly(vinyl alcohol) need be fully hydrolyzed but may contain some lower hydrolyzed material, e.g., a hydrolysis value of from 85 to 90% at a molecular weight greater than 15,000. If some lower hydrolysis material is employed, the level should be monitored closely as the emulsion will become less stable. One may use from 0 to 25% of such lower hydrolysis poly(vinyl alcohol) but the remainder of the poly(vinyl alcohol) should have a hydrolysis value of at least 98% as the other component of the stabilizer.

[0021] Another of the keys in producing a stable lower alkyl acrylate containing emulsion lies in the use of a chain transfer agent. These chain transfer agents are incorporated in an amount of from 0.2 to 3% and, preferably from 0.5 to 1.5%, by weight of the monomers to be polymerized. Representative chain transfer agents include conventional mercaptans such as *n*-dodecylmercaptan and water soluble chain transfer agents. Typically, these chain transfer agents should have a chain transfer coefficient of at least 0.6 based upon methylmethacrylate.

[0022] Emulsion polymerization of the lower alkyl esters of acrylic and methacrylic acid in the presence of poly(vinyl alcohol) and a chain transfer agent can be carried out using conventional delay addition polymerization techniques or by the conventional batch method. In the delay procedure, which is preferred, from 10 to 30% of the monomers to be polymerized are added to the polymerization reactor containing a stabilizer and the balance of the monomers added over a period of time. The time for addition may vary but a conventional procedure will add the monomers over a period of from 2 to 4 hours. A further description is set forth in U.S. Patent 5,326,809.

[0023] As in conventional emulsion polymerization processes the catalyst used is a free-radical forming catalyst such as a peroxide e.g. *t*-butyl hydroperoxide, persulfate such as potassium persulfate and ammonium persulfate as well as azo compounds e.g. 2,2'-azo bis amidino propane hydrochloride and reducing systems such as sodium formaldehyde sulfoxylate and sodium erythrobate. The oxidizing agent is generally employed on an amount of from 0.01 to 1% preferably 0.05 to 0.5% based on the weight of the monomers introduced into the polymerization system. The reducing agent is added as an aqueous system and in the necessary equivalent or stoichiometric amount.

[0024] The particle size of the acrylic polymers and copolymers in the emulsion is in the range of 0.3 to 2 microns. This particle size range has advantages over the extreme fine particle size emulsions obtained through microfluidization. These advantages comprises stability under high shear, wet tack, setting speeds, stability to salts and wide formulation range offering latitude to formulators.

[0025] One of the significant advantages of the lower alkyl acrylate emulsions described herein is that they are stabilized with a stabilizing system consisting essentially of the fully hydrolyzed poly(vinyl alcohol) and/or partially hydrolyzed poly(vinyl alcohols), as described, do not contain levels of nonionic and anionic surfactants which may adversely affect the properties of the resulting polymer in many applications. Property advantages associated with the polymer in the presence of the fully hydrolyzed poly(vinyl alcohol) include those mentioned, supra, and desirable emulsion viscosity. Prior art emulsions having high levels of poly(vinyl alcohol) tend to have large levels of grafting which contributes to process disadvantages associated with undesirable viscosity, poor film formation and water resistance.

EP 0 812 863 B1

The emulsions stabilized with lower levels of poly(vinyl alcohol) provide improvement in these properties.

[0026] The following examples are provided to illustrate various embodiments of the invention. All quantities are in parts by weight unless otherwise specified.

5 Example 1

Hydrolysis of Poly(vinyl acetate)

[0027] The following method was used to determine the extent of hydrolysis of the poly(vinyl alcohol) samples used in the examples. A weighed sample of the poly(vinyl alcohol) was placed into a flask and dissolved in a 75/25 volume/ volume mixture of water and methanol. An aliquot of sodium hydroxide solution of known concentration was then added in an amount sufficient to completely hydrolyze all remaining acetate groups. The solutions were then refluxed for one hour to insure complete reaction. Finally, the extent of hydrolysis was determined by back titration of excess sodium hydroxide with a standardized acid solution. The amount of sodium hydroxide consumed in completing the hydrolysis of the poly(vinyl alcohol) was then used to determine the hydrolysis extent of the poly(vinyl alcohol).

Example 2

Preparation of Butyl Acrylate/Methylmethacrylate Emulsions In the Presence of Poly(vinyl alcohol)

[0028] General synthesis procedure: A 2 liter jacketed glass reactor equipped with a mixer, condenser, nitrogen purge and feeds for solution addition is used as the polymerization vessel. An aqueous system consisting of an initial charge which consists of water, stabilizing agent, oxidizing agent, a small level (10 to 30%) of monomer and promoter. This mixture is heated to reaction temperature and allowed to equilibrate at the desired temperature. The reaction then is initiated by addition of a small amount of reducing agent. When reaction begins to generate heat, addition of the feeds (delay addition) is commenced. The desired reaction temperature is maintained by heating or cooling the jacket of the reactor and by controlling the addition rate of the delay components. After all of the monomer and initiator solutions are added, the products are maintained at the reaction temperature for 30 to 90 minutes to insure complete conversion of monomer. The products were then cooled to room temperature and removed.

[0029] Emulsions, A through F, based upon butyl acrylate and methylmethacrylate were prepared in accordance utilizing the above general description. The examples, A through F, differed primarily through the use of various poly (vinyl alcohol) polymers as the stabilizer, such poly(vinyl alcohol) polymers being designated A-F to correspond to the different emulsions. Poly(vinyl alcohols) A-F are described in the following table.

Poly(vinyl alcohol)		
Poly(vinyl alcohol)	Number Average Molecular Weight	Degree of Hydrolysis (mole %)
A	6,000	97.4
B	7,000-13,000	98-98.8
C	27,000-44,000	96.5-97.5
D-comparative	7,000-13,000	96.7
E-comparative	44,000-65,000	95.5-96.5
F-comparative	15,000-27,000	87-89
G	15,000-27,000	98-98.8

Emulsion (Poly(vinyl alcohol) A

[0030] This example illustrates the preparation of a butyl acrylate/methylmethacrylate copolymer emulsion prepared in the presence of poly(vinyl alcohol) A as the only stabilizer.

Initial Charge to Reactor	
Deionized water	230 gms
poly(vinyl alcohol) A 10% aqueous solution	340 gms

EP 0 812 863 B1

(continued)

Initial Charge to Reactor	
Monomer mixture (same ratio as below)	357 gms
tert butylhydroperoxide (70% aq soln)	1.0 gms
Ferrous ammonium sulfate (1% aq soln)	5 gms
acetic acid	3.9 gms

Delay Feeds	
Solutions	Amount
1) Deionized water	323.4 gms
Sodium formaldehyde sulfoxylate	6.6 gms
Total	330 gms
2) Deionized water	169.5 gms
tert butylhydroperoxide (70% aq soln)	10.65 gms
Foamaster VF*	1.5
Total	181.65 gms
3) <u>n</u> -butyl acrylate	383 gms
methylmethacrylate	467 gms
<u>n</u> -dodecyl mercaptan	7 gms
Total	857 gms

Foamaster VF is a commercial defoamer.

[0031] The reaction was conducted at 70°C. Delay solution 1 was added at a rate of 0.2 gm/min initially followed by an increase to 1.9 gm/min over a 2 hour period. Delay solution 2 was added at a rate of 0.1 gm/min initially then increased to 0.5 gm/min after 15 minutes. The monomer delay solution 3 was added at a rate of 3.3 gm/min. The reaction was complete in 4 hours. The product had the following properties.

Unreacted Monomer butyl acrylate	39 ppm
methylmethacrylate	133 ppm
% Solids	49.5
Accelerated Sedimentation.	4.0%
pH	3.2
Tg	12.1°C
60 RPM Visc	225 cps
12 RPM Visc.	420 cps
100 mesh grits	2500 ppm

Viscosity measured on 4% emulsion, Brookfield instrument.

[0032] The emulsion was stable thus showing that high solids, butyl acrylate/methylmethacrylate emulsions could be prepared using poly(vinyl alcohol) as the only stabilizer. Grit levels were modest.

Emulsion (Poly(vinyl alcohol) B

[0033] This example illustrates the preparation of a butyl acrylate/methylmethacrylate copolymer emulsion prepared

EP 0 812 863 B1

in the presence of poly(vinyl alcohol) B as having a hydrolysis value of 98% to 98.8%.

Initial Charge to Reactor	
Deionized water	230 gms
poly(vinyl alcohol) B 10% aqueous solution	340 gms
Monomer mixture (same ratio as below)	357 gms
tert butylhydroperoxide (70% aq soln)	1.0 gms
Ferrous ammonium sulfate (1% aq soln)	5 gms
acetic acid	6.2 gms

Delay Feeds	
Solutions	Amount
1) Deionized water	323.4 gms
Sodium formaldehyde sulfoxylate	6.6 gms
Total	330 gms
2) Deionized water	169.5 gms
tert butylhydroperoxide (70% aq soln)	10.65 gms
Foamaster VF*	1.5
Total	181.65 gms
3) <u>n</u> - butyl acrylate	383 gms
methylmethacrylate	467 gms
<u>n</u> - dodecyl mercaptan	7 gms
Total	857 gms

[0034] The reaction was conducted at 70°C. Delay solution 1 was added at a rate of 0.5 gm/min initially followed by an increase to 1.3 gm/min over a 1.5 hour period. Delay solution 2 was added at a rate of 0.3 gm/min initially then increased to 0.7 gm/min after 15 minutes. The monomer delay solution 3 was added at a rate of 3.7 gm/min. The reaction was complete in 4 hours. The product had the following properties.

Unreacted Monomer butyl acrylate	80 ppm
methylmethacrylate	140 ppm
% Solids	49
pH	3.1
Tg	20.9°C
12 RPM Visc	ND
60 RPM Visc	265 cps
100 mesh grits	100 ppm
Accelerated Sedimentation.	3.0%

[0035] The emulsion was stable and had few grits thus showing the effectiveness of the poly(vinyl alcohol) B as a stabilizer. It is believed the higher molecular weight poly(vinyl alcohol), i.e., 7000 to 13,000, as compared to that of poly(vinyl alcohol) A, is the main cause for the decreased grit level. That result is believed due to greater stabilizing forces within the higher molecular weight alcohol.

EP 0 812 863 B1

Emulsion (Poly(vinyl alcohol) C

[0036] This example demonstrates the preparation of a butyl acrylate/methylmethacrylate copolymer emulsion in the presence of poly(vinyl alcohol) C (96.5 to 97.5% hydrolysis) as the only stabilizer.

Initial Charge to Reactor	
Deionized water	230 gms
Poly(vinyl alcohol) C 10% aqueous solution	340 gms
Monomer mixture (same ratio as below)	357 gms
Tert butylhydroperoxide (70% aq soln)	1.0 gms
Ferrous ammonium sulfate (1% aq soln)	5 gms
Acetic acid	3.1 gms

Delay Feeds	
Solution	Amount
1) Deionized water	323.4 gms
Sodium formaldehyde sulfoxylate	6.6 gms
Total	330 gms
2) Deionized water	169.5 gms
tert-butylhydroperoxide (70% aq soln)	10.65 gms
Foamaster VF*	1.5
Total	181.65 gms
3) <u>n</u> -butyl acrylate	383 gms
methylmethacrylate	467 gms
<u>n</u> -dodecyl mercaptan	7 gms
Total	857 gms

[0037] The reaction was conducted at 70°C. Delay solution 1 was added at a rate of 0.2 gm/min initially followed by an increase to 1.2 gm/min over a 2-hour period. Delay solution 2 was added at a rate of 0.1 gm/min initially then increased to 0.7 gm/min over 30 minutes. The monomer delay solution 3 was added at a rate of 3.6 gm/min. The reaction was complete in 4 hours. The product had the following properties.

Unreacted Monomer butyl acrylate	49 ppm
methylmethacrylate*	ND
% Solids	50.3
pH	4.0
Tg	22°C
12 RPM Visc	19000 cps
60 RPM Visc	7980 cps
Accelerated Sedimentation	7.0%
100 mesh grits	1900 ppm
ND = not detected	

[0038] The results show that the poly(vinyl alcohol) was effective for stabilizing the acrylic monomer system. However,

EP 0 812 863 B1

as compared to poly(vinyl alcohol) B there was higher viscosity and grit formation probably due to the lower hydrolysis values of the poly(vinyl alcohol).

Emulsion (Poly(vinyl alcohol) D

[0039] This example illustrates the preparation of a butyl acrylate/methylmethacrylate copolymer emulsion prepared in the presence of poly(vinyl alcohol) D having a hydrolysis of 96.7% as the only stabilizer.

Initial Charge to Reactor	
Deionized water	230 gms
Poly(vinyl alcohol) D 10% aqueous solution	340 gms
Monomer mixture (same ratio as below)	357 gms
Tert butylhydroperoxide (70% aq soln)	1.0 gms
Ferrous ammonium sulfate (1% aq soln)	5 gms
Acetic acid	4.8 gms

Delay Feeds	
Solution	Amount
1) Deionized water	323.4 gms
Sodium formaldehyde sulfoxylate	6.6 gms
Total	330 gms
2) Deionized water	169.5 gms
tert-butylhydroperoxide (70% aq soln)	10.65 gms
Foamaster VF*	1.5
Total	181.65 gms
3) <u>n</u> -butyl acrylate	383 gms
methylmethacrylate	467 gms
<u>n</u> -dodecyl mercaptan	7 gms
Total	857 gms

[0040] The reaction was conducted at 70°C. Delay solution 1 was added at a rate of 0.2 gm/min initially followed by an increase to 1.9 gm/min over a 2 hour period. Delay solution 2 was added at a rate of 0.1 gm/min initially then increased to 0.6 gm/min after 15 minutes. The monomer delay solution 3 was added at a rate of 3.3 gm/min. Large amounts of coagulum were observed immediately upon initiation of the reaction. This instability persisted throughout the reaction. The reaction was complete in 4 hours. The product had the following properties.

Unreacted Monomer butyl acrylate	24 ppm
methylmethacrylate	63 ppm
% Solids	ND
Accelerated Sedimentation	ND
pH	ND
Tg	ND
12 RPM Visc	ND
60 RPM Visc	ND

EP 0 812 863 B1

(continued)

100 mesh grits	ND
ND - Not determined due to instability of the product.	

[0041] As noted from the description, the polymer coagulated almost immediately and the lower hydrolysis value of the poly(vinyl alcohol) was believed to be the basis for the ineffectiveness of the poly(vinyl alcohol) as a stabilizer. The presence of chain transfer agent did not help. It is believed the results obtained here are somewhat spurious because the data can not be reconciled with other work. Please refer to Example 5 regarding the Test Summary. However, the poly(vinyl alcohol) employed is on the borderline of acceptable stabilizers and one may expect upsets.

Emulsion (Poly(vinyl alcohol) E

[0042] This example illustrates the preparation of a butyl acrylate/methylmethacrylate copolymer emulsion prepared in the presence of poly(vinyl alcohol) E as the only stabilizer.

Initial Charge to Reactor	
Deionized water	230 gms
Poly(vinyl alcohol) E 10% aqueous solution	340 gms
Monomer mixture (same ratio as below)	357 gms
Tert butylhydroperoxide (70% aq soln)	1.0 gms
Ferrous ammonium sulfate (1% aq soln)	5 gms
Acetic acid	3.3 gms

Delay Feeds	
Solution	Amount
1) Deionized water	323.4 gms
Sodium formaldehyde sulfoxylate	6.6 gms
2) Deionized water	169.5 gms
tert-butylhydroperoxide (70% aq soln)	10.65 gms
Foamaster VF*	1.5
3) <u>n</u> -butyl acrylate	383 gms
methylmethacrylate	467 gms
<u>n</u> -dodecyl mercaptan	7 gms

[0043] The reaction was conducted at 70°C. Delay solution 1 was added at a rate of 0.2 gm/min initially followed by an increase to 1.9 gm/min over a 2 hour period. Delay solution 2 was added at a rate of 0.1 gm/min initially then increased to 0.6 gm/min after 15 minutes. The monomer delay solution 3 was added at a rate of 3.3 gm/min. Large amounts of coagulum were observed immediately upon initiation of the reaction. This instability persisted throughout the reaction. The reaction was stopped after 2 hours. The product had the following properties.

Unreacted Monomer butyl acrylate	43 ppm
methylmethacrylate	238 ppm
% Solids	34%
Accelerated Sedimentation.	ND

EP 0 812 863 B1

(continued)

pH	2.7
Tg	ND
12 RPM Visc	ND
60 RPM Visc	ND
100 mesh grits	49,000 ppm
ND - Not determined due to instability of the product.	

[0044] The ineffectiveness of the high molecular weight, low hydrolysis poly(vinyl alcohol) as the stabilizer confirms the results of prior investigators regarding the ability of poly(vinyl alcohol) to stabilize the more water insoluble acrylic monomers in the absence of other hydrophilic monomers and/or stabilizers.

Emulsion (Poly(vinyl alcohol) F

[0045] This example illustrates the preparation of a butyl acrylate/methylmethacrylate copolymer emulsion prepared in the presence of poly(vinyl alcohol) F as the only stabilizer.

Initial Charge to Reactor	
Deionized water	245 gms
Poly(vinyl alcohol) F 10% aqueous solution	218 gms
Monomer mixture (same ratio as below)	40 gms
Tert butylhydroperoxide (70% aq soln)	0.5 gms
Ferrous ammonium sulfate (1% aq soln)	5 gms
Acetic acid	2.3 gms

Delay Feeds	
Solution	Amount
1) Deionized water	237.5 gms
Sodium formaldehyde sulfoxylate	12.5 gms
Total	250 gms
2) Deionized water	200 gms
tert-butylhydroperoxide (70% aq soln)	8.0 gms
Total	208 gms
3) <u>n</u> butyl acrylate	289 gms
methylmethacrylate	193 gms
<u>n</u> dodecyl mercaptan	1.5 gms
Total	483.5 gms

[0046] The reaction was conducted at 70°C. Delay solution 1 was added at a rate of 0.2 gm/min initially followed by an increase to 0.3 gm/min over a 2 hour period. Delay solution 2 was added at a rate of 0.1 gm/min initially then increased to 0.4 gm/min after 15 minutes. The monomer delay was added at a rate of 1.4 gm/min. Large amounts of coagulum were observed immediately upon initiation of the reaction. This instability persisted throughout the reaction. The reaction was complete in 6 hours. The product had the following properties.

Unreacted Monomer butyl acrylate	172 ppm
----------------------------------	---------

EP 0 812 863 B1

(continued)

methylmethacrylate*	
% Solids	39.5
Accelerated Sedimentation.	ND
pH	2.3
Tg	-7.0
12 RPM Visc	ND
60 RPM Visc	ND
100 mesh grits	ND

*Not detected

ND - Not determined due to instability of the product.

[0047] The product was unstable thus slowing the importance of using a poly(vinyl alcohol) having a hydrolysis value of at least 96.5%, even though the molecular weight of the poly(vinyl alcohol) was within a desirable range.

Example 3

Batch Process For Producing Butyl acrylate/Methylmethacrylate Emulsion

[0048] This example demonstrates the preparation of a butyl acrylate/methylmethacrylate copolymer emulsion prepared in the presence of poly(vinyl alcohol) B as the only stabilizer using a by a batch process as distinguished from the delay process used in Example 2.

Initial Charge to reactor	
Deionized water	140 gms
poly(vinyl alcohol) B 10% aqueous solution	160 gms
methylmethacrylate	158 gms
butyl acrylate	141 gms
n dodecylmercaptan	0.9 gms
tert butylhydroperoxide (70% aq soln)	2.3 gms
Ferrous ammonium sulfate (1% aq soln)	5 gms
Foamaster VF	2.3 gms

Delay Feeds	
Solution	Amount
1) Deionized water	237.5 gms
Sodium formaldehyde sulfoxylate	12.5 gms
Total	250

[0049] The reaction was initiated at 40 °C and ramped to 70 °C over 1 hour. Delay solution 1 was added at a rate of 0.3 gm/min. The reaction temperature was controlled by variation of the rate of addition of delay solution 1. The reaction was complete in 2 hours. The product exhibited good stability throughout the process. The product had the following properties.

Unreacted Monomer butyl acrylate	31 ppm
methylmethacrylate *	
% Solids	45.8

* Not detected

EP 0 812 863 B1

(continued)

Accelerated Sedimentation.	4.0%
pH	--
60 RPM Visc	--
Tg 1	-3.3
12 RPM Visc	--
100 mesh grits	--

Example 4

Preparation of Butyl Acrylate/Methylmethacrylate Emulsions

In the Presence of Blend of Poly(vinyl alcohols)

[0050] This example demonstrates the preparation of a butyl acrylate/methylmethacrylate copolymer emulsion prepared in the presence of a mixture or blend of poly(vinyl alcohol) C and poly(vinyl alcohol) G as the stabilizer.

Initial Charge to reactor	
Deionized water	403 gms
poly(vinyl alcohol) C 10% aqueous solution	619 gms
poly(vinyl alcohol) G 10% aqueous solution	185 gms
Monomer mixture (same ratio as below)	434 gms
tert butylhydroperoxide (70% aq soln)	2.2 gms
Ferrous ammonium sulfate (5% aq soln)	5 gms
acetic acid	5.8 gms

Delay Feeds	
Solution	Amount
1) Deionized water	393.9 gms
Sodium formaldehyde sulfoxylate	10.1 gms
Total	404 gms
2) Deionized water	387 gms
tert butylhydroperoxide (70% aq soln)	15.4 gms
Total	402.4 gms
3) n-butyl acrylate	935 gms
methylmethacrylate	935 gms
n-dodecyl mercaptan	13.2 gms
Total	1883.2 gms

[0051] The reaction was conducted at 70° C. Delay solutions 1 and 2 were added at a rate of 0.3 gm/min initially followed by an increase to 1.7 gm/min over a 2 hour period. The monomer delay was added at a rate of 16.1 gm/min. The reaction was complete in 2.5 hours. Of the total amounts of delay solutions 1 and 2 shown above, the actual amounts used were delay solution 1, 105.1 gms and delay solution 2, 156.9 gms. Additional water was added to adjust the final solids content to ~50%. The product had the following properties.

EP 0 812 863 B1

Unreacted Monomer, butyl acrylate methylmethacrylate *	235 ppm
% Solids	50.4
Accelerated Sedimentation.	3.0 %
pH	3.9
60 RPM Visc	2400 cps
Tg 1	0.7 °C
12 RPM Visc	5400 cps
100 mesh grits	50 ppm

* Not detected

[0052] This example indicates the good properties which can be achieved through the use of combinations of poly (vinyl alcohol) polymers with differing molecular weight and hydrolysis levels. Grit formation was less than with any of the poly(vinyl alcohol) types used singly.

Example 5

Test Summary

[0053] A series of tests were conducted to determine the effectiveness of a wide variety of commercial poly(vinyl alcohols). The general procedure of Example 1 was followed. The poly(vinyl alcohols) are described in the following table.

PVOH Tested	% Hydrolysis	Viscosity/ Number avg. Molecular Weight	Effective in Acrylate stabilization
A-502	87-89	3.0-3.7/ 7,000-13,000	Yes, high viscosity
A-203	87-89	3.0-4.5/ 7,000-15,000	Yes
A-205	87-89	5.2-6.2/ 15,000-27,000	No- gritty and high sed
A-523	87-89	23-27/ 44,000-65,000	No- gritty and high sed
WS-42	96.5-97.5	14-17/ 27,000-44,000	Yes
A- 425	95.5-96.5	27-31/ 44,000-65,000	No- gritty, high viscosity and high sed
A-103	98.0-98.8	3.5-4.5/ 7,000-15,000	Yes
A-107	98.0-98.8	5.5-6.6/ 15,000-27,000	Yes
A-321	98.0-98.8	16.5-20.5/ 27,000-44,000	Yes
A-125	99.3 +	28-32/ 44,000-65,000	Yes
Run 1	97.6	2.6/ 6,000	Yes
Run 2	97.2	2.4/ 5,000	Yes

A in the above table is an abbreviation for the trademark, Airvol, owned by Air Products and Chemicals, Inc. for its line of poly(vinyl alcohols). The number following in the grade designation. Sed is an abbreviation for sedimentation.

[0054] As can be gleaned from the table, the best results are obtained with the medium weight, high hydrolysis >98% poly(vinyl alcohols). The results also show that the low hydrolysis poly(vinyl alcohol) at the low molecular weight was effective in stabilizing the acrylic emulsion and is in contrast to poly(vinyl alcohol) D, supra.

Comparative Example 1

[0055] In this specific example a butyl acrylate/methylmethacrylate copolymer emulsion was prepared in accordance with the procedure of Example using poly(vinyl alcohol) B as the only stabilizer, the difference being the omission of the chain transfer agent, dodecyl mercaptan. The polymerization was terminated after a few hours because of excessive grit formation and emulsion instability.

Claims

1. A process for the emulsion polymerization of a monomer mixture consisting essentially of water insoluble, ethylenically unsaturated monomers having acrylic unsaturation for producing polyacrylic polymer particles wherein a polymerizable monomer system consisting essentially of at least one acrylic monomer is polymerized in the presence of water and a stabilizer for producing polyacrylic polymer, the improvement for producing an acrylic emulsion having a solids content of greater than 45% by weight without microfluidization which comprises:
 - a) effecting the polymerization in a polymerization zone utilizing a stabilizer consisting essentially of poly(vinyl alcohol) selected from the group consisting of poly(vinyl alcohol) having a hydrolysis value of greater than 96.5% and a poly(vinyl alcohol) having a hydrolysis value of at least 86% where the molecular weight is within a range of from 5,000 to 13,000 and in the substantial absence of surfactants and solvents, said poly(vinyl alcohol) being present in an amount of from 2 to 15% by weight of the monomers to be polymerized; and,
 - b) effecting the polymerization in the presence of a chain transfer agent.
2. The process of Claim 1 wherein the poly(vinyl alcohol) is incorporated in the emulsion in an amount of from 3 to 7% by weight of the monomers polymerized.
3. The process of Claim 2 wherein the chain transfer agent is incorporated in an amount of from 0.2 to 3% by weight of the monomers to be polymerized.
4. The process of Claim 3 wherein the polymerization is effected by delay addition of the acrylic monomer to the polymerization zone.
5. The process of Claim 4 wherein the delay addition is effected by charging from 10 to 30% of the acrylic monomer to be polymerized as an initial charge to the polymerization zone and then adding the balance of the monomer over a period of time.
6. The process of Claim 3 wherein the acrylic monomers are C₁₋₈ alkyl esters of acrylic and methacrylic acid.
7. The process of Claim 6 wherein the acrylic monomers are selected from the group consisting of methylmethacrylate, ethylacrylate, ethylmethacrylate, butyl acrylate, 2-ethyl-hexyl acrylate.
8. The process of Claim 6 wherein the poly(vinyl alcohol) has a percent hydrolysis of at least 98%.
9. The process of Claim 7 wherein the poly(vinyl alcohol) stabilizer is present as a blend comprising from 20 to 80% of a low molecular weight (5,000 to 13,000) poly(vinyl alcohol) and 20 to 80% of a higher molecular weight 25,000 to 45,000 poly(vinyl alcohol).
10. The process of Claim 9 wherein the poly(vinyl alcohol) stabilizer is present in an amount of from 50 to 75% of a low molecular weight (5,000 to 13,000) poly(vinyl alcohol) and a hydrolysis value of from 86 to 90% and 25 to 50% of a higher molecular weight 25,000 to 45,000 poly(vinyl alcohol).
11. An aqueous emulsion consisting essentially of polymerized ethylenically unsaturated monomers having acrylic unsaturation for producing polyacrylic polymer particles, the improvement which comprises: said emulsion stabilized with a stabilizer consisting essentially of poly(vinyl alcohol) selected from the group consisting of poly(vinyl alcohol) having a hydrolysis value of greater than 96.5% and a poly(vinyl alcohol) having a hydrolysis value of at least 86% where the molecular weight is within a range of from 5,000 to 13,000 and said emulsion is substantially free of surfactants and solvents, said emulsion having a solids content of at least 45% by weight of the emulsion and the poly(vinyl alcohol) being incorporated in an amount of from 2 to 12% by weight of the polyacrylic polymers.
12. The emulsion of Claim 11 wherein the poly(vinyl alcohol) is incorporated in the emulsion in an amount of from 3 to 7% by weight of the monomers polymerized.
13. The emulsion of Claim 12 wherein the chain transfer agent is incorporated in an amount of from 0.2 to 3% by weight of the monomers to be polymerized.
14. The emulsion of Claim 13 wherein the acrylic monomers are C₁₋₈ alkyl esters of acrylic and methacrylic acid and

the chain transfer is a mercaptan.

15. The emulsion of Claim 14 wherein the acrylic monomers are selected from the group consisting of methylmethacrylate, ethylacrylate, ethylmethacrylate, butyl acrylate, 2-ethyl-hexyl acrylate.
16. The emulsion of Claim 15 wherein the poly(vinyl alcohol) has a percent hydrolysis of at least 98%.
17. The emulsion of Claim 15 wherein the poly(vinyl alcohol) stabilizer is present in an amount of from 20 to 80% of a low molecular weight (5000 to 13,000) poly(vinyl alcohol) and 20 to 80% of a higher molecular weight 25,000 to 45,000 poly(vinyl alcohol).
18. The emulsion of Claim 16 wherein the poly(vinyl alcohol) stabilizer is present in an amount of from 50 to 75% of a low molecular weight (5000 to 15,000) poly(vinyl alcohol) and 25 to 50% of a higher molecular weight 25,000 to 45,000 poly(vinyl alcohol).
19. A redispersible acrylic polymer formed from the emulsion of any of claims 11 to 18.

Patentansprüche

1. Verfahren zur Emulsionspolymerisation eines Monomergemisches, das im wesentlichen aus wasserunlöslichen, ethylenisch ungesättigten Monomeren, die acrylische Ungesättigtheit aufweisen, besteht, zur Herstellung von Polyacrylpolymerpartikeln, in dem ein polymerisierbares Monomersystem, das im wesentlichen aus wenigstens einem Acrylmonomer besteht, in Anwesenheit von Wasser und einem Stabilisator zur Herstellung eines Polyacrylpolymeres polymerisiert wird, wobei die Verbesserung zur Herstellung einer Acrylemulsion, die einen größeren Feststoffgehalt als 45 Gewichtsprozent hat, ohne Mikrofluidisation:
 - a) das Bewirken der Polymerisation in einer Polymerisationszone unter Verwendung eines Stabilisators, der im wesentlichen aus Polyvinylalkohol besteht, der aus der Gruppe ausgewählt wurde, die aus Polyvinylalkohol mit einem Hydrolysewert größer als 96,5 % und einem Polyvinylalkohol mit einem Hydrolysewert von wenigstens 86 %, wo das Molekulargewicht in einem Bereich von 5.000 bis 13.000 ist, besteht, und im wesentlichen unter Abwesenheit von Tensiden und Lösungsmitteln, wobei besagter Polyvinylalkohol in einer Menge von 2 bis 15 Gewichtsprozent des zu polymerisierenden Monomers vorliegt, und
 - b) das Bewirken der Polymerisation in Anwesenheit eines Kettenübertragungsmittels umfaßt.
2. Das Verfahren nach Anspruch 1, dadurch gekennzeichnet, daß der Polyvinylalkohol in einer Menge von 3 bis 7 Gewichtsprozent der polymerisierten Monomere in der Emulsion enthalten ist.
3. Das Verfahren nach Anspruch 2, dadurch gekennzeichnet, daß das Kettenübertragungsmittel in einer Menge von 0,2 bis 3 Gewichtsprozent der zu polymerisierenden Monomere enthalten ist.
4. Das Verfahren nach Anspruch 3, dadurch gekennzeichnet, daß die Polymerisation durch verzögerte Zugabe des Acrylmonomers zu der Polymerisationszone bewirkt wird.
5. Das Verfahren nach Anspruch 4, dadurch gekennzeichnet, daß die verzögerte Zugabe durch Eintragen von 10 bis 30 % des zu polymerisierenden Acrylmonomers als Ausgangseintrag zu der Polymerisationszone und dann Zugabe des Hauptgewichtes des Monomers über einen Zeitraum bewirkt wird.
6. Das Verfahren nach Anspruch 3, dadurch gekennzeichnet, daß die Acrylmonomere C₁₋₈-Alkylester der Acryl- und Methacrylsäure sind.
7. Das Verfahren nach Anspruch 6, dadurch gekennzeichnet, daß die Acrylmonomere aus der Gruppe ausgewählt werden, die aus Methylmethacrylat, Ethylacrylat, Ethylmethacrylat, Butylacrylat, 2-Ethylhexylacrylat besteht.
8. Das Verfahren nach Anspruch 6, dadurch gekennzeichnet, daß der Polyvinylalkohol einen Hydrolysegrad von wenigstens 98 % hat.
9. Das Verfahren nach Anspruch 7, dadurch gekennzeichnet, daß der Polyvinylalkohol-Stabilisator als Gemisch vor-

liegt, das 20 bis 80 % eines Polyvinylalkohols mit niedrigem Molekulargewicht (5.000 bis 13.000) und 20 bis 80 % eines Polyvinylalkohols mit höherem Molekulargewicht von 25.000 bis 45.000 umfaßt.

- 5 10. Das Verfahren nach Anspruch 9, dadurch gekennzeichnet, daß der Polyvinylalkohol-Stabilisator in einer Menge von 50 bis 75 % eines Polyvinylalkohols mit niedrigem Molekulargewicht (5.000 bis 13.000) und einem Hydrolysewert von etwa 86 bis 90 % und 25 bis 50 % eines Polyvinylalkohols mit höherem Molekulargewicht von 25.000 bis 45.000 vorliegt.
- 10 11. Wässrige Emulsion, die im wesentlichen aus polymerisierten ethylenisch ungesättigten Monomeren, die acrylische Ungesättigtheit aufweisen, besteht, zur Herstellung von Polyacrylpolymerpartikeln, wobei die Verbesserung besagte Emulsion umfaßt, die mit einem Stabilisator stabilisiert ist, der im wesentlichen aus Polyvinylalkohol besteht, der aus der Gruppe ausgewählt wurde, die aus Polyvinylalkohol mit einem Hydrolysewert größer als 96,5 % und einem Polyvinylalkohol mit einem Hydrolysewert von wenigstens 86 %, wo das Molekulargewicht in einem Bereich von 5.000 bis 13.000 ist, besteht, und besagte Emulsion im wesentlichen frei von Tensiden und Lösungsmitteln ist, besagte Emulsion einen Feststoffgehalt von wenigstens 45 Gewichtsprozent der Emulsion hat und der Polyvinylalkohol in einer Menge von 2 bis 12 Gewichtsprozent des Polyacrylpolymeren enthalten ist.
- 15 12. Die Emulsion nach Anspruch 11, dadurch gekennzeichnet, daß der Polyvinylalkohol in der Emulsion in einer Menge von 3 bis 7 Gewichtsprozent der polymerisierten Monomere enthalten ist.
- 20 13. Die Emulsion nach Anspruch 12, dadurch gekennzeichnet, daß das Kettenübertragungsmittel in einer Menge von 0,2 bis 3 Gewichtsprozent der zu polymerisierenden Monomere enthalten ist.
- 25 14. Die Emulsion nach Anspruch 13, dadurch gekennzeichnet, daß die Acrylmonomere C₁₋₈-Alkylester der Acryl- und Methacrylsäure sind und der Kettenüberträger ein Mercaptan ist.
15. Die Emulsion nach Anspruch 14, dadurch gekennzeichnet, daß die Acrylmonomere aus der Gruppe ausgewählt werden, die aus Methylmethacrylat, Ethylacrylat, Ethylmethacrylat, Butylacrylat, 2-Ethylhexylacrylat besteht.
- 30 16. Die Emulsion nach Anspruch 15, dadurch gekennzeichnet, daß der Polyvinylalkohol einen Hydrolysegrad von wenigstens 98 % hat.
17. Die Emulsion nach Anspruch 15, dadurch gekennzeichnet, daß der Polyvinylalkohol-Stabilisator in einer Menge von 20 bis 80 % eines Polyvinylalkohols mit niedrigem Molekulargewicht (5.000 bis 13.000) und 20 bis 80 % eines Polyvinylalkohols mit höherem Molekulargewicht von 25.000 bis 45.000 vorliegt.
- 35 18. Die Emulsion nach Anspruch 16, dadurch gekennzeichnet, daß der Polyvinylalkohol-Stabilisator in einer Menge von 50 bis 75 % eines Polyvinylalkohols mit niedrigem Molekulargewicht (5.000 bis 15.000) und 25 bis 50 % eines Polyvinylalkohols mit höherem Molekulargewicht von 25.000 bis 45.000 vorliegt.
- 40 19. Ein wiederdispersierbares Acrylpolymer, das aus der Emulsion nach jedem der Ansprüche 11 bis 18 gebildet wurde.

45 Revendications

1. Procédé pour la polymérisation en émulsion d'un mélange monomère consistant essentiellement en monomères insaturés éthyléniquement, insolubles dans l'eau ayant une insaturation acrylique pour produire des particules de polymère polyacrylique, dans lequel un système monomère polymérisable consistant essentiellement en au moins un monomère acrylique est polymérisé en présence d'eau et d'un stabilisant pour produire un polymère polyacrylique, le perfectionnement pour produire une émulsion acrylique ayant une teneur en matières solides supérieure de 45% en poids sans microfluidisation et qui comprend les étapes consistant à :

a) effectuer la polymérisation dans une zone de polymérisation utilisant un stabilisant consistant essentiellement en alcool de polyvinyle choisi dans le groupe constitué par l'alcool de polyvinyle ayant une valeur d'hydrolyse supérieure à 96,5% et un alcool de polyvinyle ayant une valeur d'hydrolyse d'au moins 86%, le poids moléculaire se situant dans une plage allant de 5000 à 13000 et en l'absence substantielle d'agents tensioactifs et de solvants, l'alcool de polyvinyle étant présent dans une quantité allant de 2 à 15% en poids des monomères

à polymériser ; et

b) effectuer la polymérisation en présence d'un agent de transfert de chaîne.

2. Procédé selon la revendication 1, dans lequel l'alcool de polyvinyle est incorporé dans l'émulsion dans une quantité allant de 3 jusqu'à 7% en poids des monomères polymérisés.
3. Procédé selon la revendication 1, dans lequel l'agent de transfert de chaîne est incorporé dans une quantité allant de 0,2 à 3% en poids des monomères à polymériser.
4. Procédé selon la revendication 3, dans lequel la polymérisation est effectuée par addition retardée du monomère acrylique à la zone de polymérisation.
5. Procédé selon la revendication 4, dans lequel l'addition retardée est effectuée en chargeant de 10 à 30% du monomère acrylique à polymériser comme charge initiale à la zone de polymérisation et à ajouter ensuite le reste de monomère au cours d'une certaine durée.
6. Procédé selon la revendication 3, dans lequel les monomères acryliques sont des alkylesters C₁₋₈ de l'acide acrylique et méthacrylique.
7. Procédé selon la revendication 6, dans lequel les monomères acryliques sont choisis dans le groupe constitué par le méthyle méthacrylate, l'éthylacrylate, l'éthylméthacrylate, le butyle acrylate, le 2-éthylhexylacrylate.
8. Procédé selon la revendication 6, dans lequel l'alcool de polyvinyle a un pourcentage d'hydrolyse d'au moins 98%.
9. Procédé selon la revendication 7, dans lequel le stabilisant d'alcool de polyvinyle est présent comme mélange comprenant de 20 à 80% d'un faible poids moléculaire (5000 à 13000) d'alcool de polyvinyle et 20 à 80% d'un poids moléculaire plus élevé 25000 à 45000 alcool de polyvinyle.
10. Procédé selon la revendication 9, dans lequel le stabilisant d'alcool de polyvinyle est présent dans une quantité de 50 à 75% d'un alcool de polyvinyle à faible poids moléculaire (5000 à 13000) et d'une valeur d'hydrolyse d'environ 86 à 90% et 25 à 50% d'un alcool de polyvinyle à poids moléculaire supérieur 25000 à 45000.
11. Emulsion aqueuse consistant essentiellement en des monomères insaturés éthyléniquement polymérisés ayant une insaturation acrylique pour produire des particules de polymères polyacryliques, le perfectionnement comprenant : ladite émulsion stabilisée avec un stabilisant consistant essentiellement en alcool de polyvinyle choisi dans le groupe constitué par l'alcool de polyvinyle ayant une valeur d'hydrolyse supérieure à 96,5% et un alcool de polyvinyle ayant une valeur d'hydrolyse d'au moins 86%, le poids moléculaire se situant dans une plage allant de 5000 à 13000 et l'émulsion étant sensiblement exempte d'agents tensioactifs et de solvants, émulsion ayant une teneur en matières solides d'au moins 45% en poids de l'émulsion et l'alcool de polyvinyle étant incorporé dans une quantité de 2 à 12% en poids des polymères polyacryliques.
12. Emulsion de la revendication 11, dans laquelle l'alcool de polyvinyle est incorporé dans l'émulsion dans une quantité de 3 à 7% en poids des monomères polymérisés.
13. Emulsion selon la revendication 12, dans laquelle l'agent de transfert de chaîne est incorporé dans une quantité de 0,2 à 3% en poids des monomères à polymériser.
14. Emulsion selon la revendication 13, dans laquelle les monomères acryliques sont des alkylesters C₁₋₈ de l'acide acrylique et méthacrylique et le transfert de chaîne est un mercaptan.
15. Emulsion selon la revendication 14, dans laquelle les monomères acryliques sont choisis dans le groupe constitué par le méthylméthacrylate, éthylacrylate, éthylméthacrylate, butyle acrylate, 2-éthylhexylacrylate.
16. Emulsion selon la revendication 15, dans laquelle l'alcool de polyvinyle a un pourcentage d'hydrolyse d'au moins 98%.
17. Emulsion selon la revendication 15, dans laquelle le stabilisant d'alcool de polyvinyle est présent dans une quantité de 20 à 80% d'un alcool de polyvinyle à faible poids moléculaire (5000 à 13000) et 20 à 80% d'un alcool de

EP 0 812 863 B1

polyvinyle à poids moléculaire supérieur 25000 à 45000.

18. Emulsion selon la revendication 16, dans laquelle le stabilisant d'alcool de polyvinyle est présent dans une quantité de 50 à 75% d'un alcool de polyvinyle à faible poids moléculaire (5000 à 15000) et 25 à 50% d'un alcool de polyvinyle à poids moléculaire supérieur 25000 à 45000.

19. Polymère acrylique redispersible formé à partir de l'émulsion selon l'une quelconque des revendications 1 à 18.

10

15

20

25

30

35

40

45

50

55

